

**PRODUCT DESCRIPTION**

Universal Pipe Coating (UPC).

Two component, ambient cure, titanium modified inorganic copolymer.

**INTENDED USES**

Suitable for protecting above-ground piping and accessories in new construction process plant operating at temperatures between -196°C (-321°F) to +650°C(1202°F).

Single specification for the corrosion protection of large amounts of process piping and accessories (e.g. valves, instrumentation and other associated OEM).

Interbond 1202UPC reduces paint complexity and overall painting costs of new construction projects.

Designed as a two coat or single coat application to carbon or stainless steel for long term corrosion protection.

Suitable for use on surfaces either uninsulated or under thermal insulation and for the protection of cryogenic piping and equipment. Not suitable for buried service.

**PRACTICAL INFORMATION FOR INTERBOND 1202UPC**

<b>Colour</b>	Metallic Grey
<b>Gloss Level</b>	Matt
<b>Volume Solids</b>	64%
<b>Typical Thickness</b>	100 - 200 microns (4-8 mils) dry equivalent to 156-313 microns (6.3-12.5 mils) wet
<b>Theoretical Coverage</b>	3.70 m <sup>2</sup> /litre at 175 microns d.f.t and stated volume solids 147 sq.ft/US gallon at 7 mils d.f.t and stated volume solids
<b>Practical Coverage</b>	Allow appropriate loss factors
<b>Method of Application</b>	Airless Spray, Air Spray, Conventional Spray
<b>Drying Time</b>	

Overcoating interval with self

Temperature	Touch Dry	Hard Dry	Minimum	Maximum
10°C (50°F)	90 minutes	16 hours	24 hours	7 days
15°C (59°F)	60 minutes	9 hours	16 hours	7 days
25°C (77°F)	30 minutes	7 hours	12 hours	7 days
40°C (104°F)	15 minutes	6 hours	10 hours	7 days

Where maximum overcoating intervals are exceeded, clean the surface of Interbond 1202UPC thoroughly with clean fresh water then lightly abrade.

**REGULATORY DATA**
**Flash Point (Typical)** Part A 32°C (90°F); Part B 22°C (72°F); Mixed 25°C (77°F)

**Product Weight** 1.28 kg/l (10.7 lb/gal)

**VOC** 3.50 lb/gal (420 g/lit) 332 g/kg  
 EPA Method 24  
 EU Solvent Emissions Directive  
 (Council Directive 1999/13/EC)

See Product Characteristics section for further details

**SURFACE PREPARATION**

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000. Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

**Abrasive Blast Cleaning**

Abrasive blast clean to Sa2½ (ISO 8501-1:2007) or SSPC-SP10. If oxidation has occurred between blasting and application of Interbond 1202UPC, the surface should be reblasted to the specified visual standard. Surface defects revealed by the blast cleaning process should be ground, filled, or treated in the appropriate manner. A surface profile of 50 microns (2 mils) is recommended.

**Power Tool Cleaning (Small Areas Only)**

For small areas of touch up and repair, Power Tool cleaning to SSPC SP11 is suitable. Optimum performance will be achieved with a minimum surface profile of 50 microns (2 mils).

**Austenitic Stainless Steel**

Ensure surface is clean, dry and free from metal corrosion products prior to application. Abrasive blast with nonmetallic and chloride free abrasive (e.g. aluminium oxide or garnet) to obtain anchor profile of 37.5 to 50 microns (1.5 to 2 mils).

Optimum performance will be achieved for steel operating under high & cyclic temperature conditions when the preferred 50 micron (2 mil) profile is obtained.

**Primed Surfaces**

Interbond 1202UPC is suitable for application to unweathered steelwork freshly coated with zinc silicate shop primers.

If the zinc shop primer shows extensive or widely scattered breakdown, or excessive zinc corrosion products, overall sweep blasting will be necessary. Other types of shop primer are not suitable for overcoating and will require complete removal by abrasive blast cleaning.

Weld seams and damaged areas should be blast cleaned to Sa2½ (ISO 8501-1:2007) or SSPC-SP6.

**APPLICATION**

<b>Mixing</b>	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.			
	(1) Agitate Base (Part A) with a power agitator.			
	(2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.			
<b>Mix Ratio</b>	54 part(s) : 1 part(s) by volume			
<b>Working Pot Life</b>	5°C (41°F)	15°C (59°F)	25°C (77°F)	40°C (104°F)
	2 hours	1.5 hours	75 minutes	50 minutes
<b>Airless Spray</b>	Recommended	Tip Range 0.38-0.48 mm (15-19 thou) Total output fluid pressure at spray tip not less than 141 kg/cm <sup>2</sup> (2005 p.s.i.)		
<b>Air Spray (Pressure Pot)</b>	Recommended when topcoating	Gun	DeVilbiss MBC or JGA	
		Air Cap	704 or 765	
		Fluid Tip	E	
<b>Air Spray (Conventional)</b>	Recommended when topcoating	Use suitable proprietary equipment		
<b>Brush</b>	Suitable - touch up only	Typically 60 microns (2.4 mils) can be achieved		
<b>Roller</b>	Suitable - touch up only	Typically 60 microns (2.4 mils) can be achieved		
<b>Thinner</b>	International GTA007	Do not thin more than allowed by local environmental legislation.		
<b>Cleaner</b>	International GTA007			
<b>Work Stoppages</b>	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA007. Once units of material have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.			
<b>Clean Up</b>	Clean all equipment immediately after use with International GTA007. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.			

All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.

**PRODUCT CHARACTERISTICS**

Interbond 1202UPC conforms to the Inert Multipolymeric Matrix coating definition as per NACE Standard Practice SP0198 Table 2 typical recommendations for use on carbon steel equipment under thermal insulation.

When applying Interbond 1202UPC in confined spaces ensure adequate ventilation.

Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Interbond 1202UPC reacts with atmospheric moisture, and as such when in the can should remain covered at all times. Failure to keep the tin covered will result in skinning of unused material and loss of pot life.

In common with many products containing leafing aluminium pigmentation Interbond 1202UPC may be prone to developing a “polished” appearance in areas of minor mechanical impact etc. However, this phenomenon is merely aesthetic and is not detrimental to the anti-corrosive performance of the product.

As with all coated surfaces, it is recommended that appropriate care be taken during storage and transport to avoid mechanical damage from dragging and scraping.

Due to the flexible nature of the coating and total recommended dry film thickness being at or below 200 microns (8 mils), pull-off adhesion testing (as per ISO 4624) is not considered relevant. Adhesion should be evaluated using cross cut methods such as those specified in ISO 2409 or ASTM D3359. Acceptable ratings achieved in practice are ≤2 (as per ISO 2409) or ≥3A (as per ASTM D3359).

When using in high heat service over inorganic zinc primer, the products should be applied in strict accordance with film thickness specifications, since application of excessive thicknesses may cause blistering. Determine that the inorganic zinc primer is thoroughly cured prior to application of the high heat coating by following the curing instructions given on the relevant product data sheet.

When using a zinc silicate primer to obtain maximum corrosion resistance the recommended thickness of zinc silicate is 50 microns (2 mils) dry film thickness to ensure maximum surface strength for any subsequent temperature cycling and to avoid flaking of topcoats

It is preferable to overcoat zinc silicate before weathering but in cases where this is not possible then the zinc silicate surface should be clean and free of zinc corrosion products.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

Low molecular weight reactive additives, which will form part of the film during normal ambient cure conditions, will also affect VOC values determined using EPA Method 24.

**SYSTEMS COMPATIBILITY**

---

Interbond 1202UPC is normally applied direct to metal. This specialist coating is only compatible with a very limited number of products.

Interzinc 22 Series

Interbond 1202UPC can be topcoated with Interthane 870 in a variety of colours including safety colours for service temperatures upto 120°C (248°F).

Interbond 1202UPC can be topcoated with Intertherm 875 or Intertherm 1875 in a limited range of colours for service temperatures between 120°C (248°F) to 205°C (401°F).

Note: The optimum topcoat appearance is achieved when Interbond 1202UPC is applied via conventional or airspray techniques.

Where overcoating is with recommended topcoats Intertherm 1875 or Intertherm 875, the maximum overcoating interval is 28 days. Where maximum overcoating intervals are exceeded, clean the surface of Interbond 1202UPC thoroughly with clean fresh water then lightly abrade.

**ADDITIONAL INFORMATION**

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at [www.international-pc.com](http://www.international-pc.com):

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage
- Interbond 1202UPC Application Guidelines

Individual copies of these information sections are available upon request.

**SAFETY PRECAUTIONS**

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	15 litre	14.73 litre	20 litre	0.27 litre	0.25 litre
	1 US gal	0.79 US gal	1 US gal	0.01 US gal	0.13 US gal
	5 US gal	3.93 US gal	5 US gal	0.07 US gal	0.25 US gal
For availability of other pack sizes, contact International Protective Coatings.					
SHIPPING WEIGHT (TYPICAL)	Unit Size	Part A		Part B	
	15 litre	20.46 kg		0.35 kg	
	1 US gal	9.1 lb		0.3 lb	
	5 US gal	45.8 lb		0.8 lb	
Consult International Protective Coatings for specific advice.					
STORAGE	Shelf Life	12 months minimum at 25°C (77°F). Store in dry, shaded conditions away from sources of heat and ignition.			

**Important Note**

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local International Paint representative that this data sheet is current prior to using the product.*

*This Technical Data Sheet is available on our website at [www.international-marine.com](http://www.international-marine.com) or [www.international-pc.com](http://www.international-pc.com), and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.*

Copyright © AkzoNobel, 07/01/2013.

 International, International and all product names mentioned in this publication are trademarks of, or licensed to, AkzoNobel.

[www.international-pc.com](http://www.international-pc.com)